

ShaliPoxy[®] 400

2K High Solid Food Grade Epoxy Coating



STP Limited

Description

ShaliPoxy[®] 400 is WRAS approved, fast setting, spray applied, solvent free, food grade, two component epoxy coating for internal / external lining of steel / concrete surface of pipes, vessels and other equipments used for portable water. **ShaliPoxy[®] 400** is spray applied by plural component airless spray gun.



ShaliPoxy[®] 400 is solvent free and is ideally suited for food grade coating where higher film thickness is required as protective barrier.

ShaliPoxy[®] 400 may be designed to meet specific physical and / or technical characteristics parameters required by the customer. The undernoted physical and / or technical parameters are of standard **ShaliPoxy[®] 400** produced by the company.

It conforms to BS : 6920:2000 and AWWA C-210.

Characteristics - Physical

Color	Grey / Light Yellow	Ratio	3:1 By Volume
Pot Life @ 28 °C, 55% RH, 100 g, minute	22 ± 3	Touch Dry @ 27 °C, 55% RH, hr	Within 1 hr
Volume Solids	100 %	Hard Dry @ 27 °C, 55% RH, hr	6-8 hours
Specific Gravity (Mixed) @ 27 °C	1.30 ± 0.20	Full Cure @ 27 °C, 55% RH, days	7
Theoretical Coverage *, m ² / L, 400 micron DFT	2.50	Application Temperature, °C	10 – 60 with RH ~ < 75%
Sagging	Passes	Cross-cut test	Passes

* Depending upon surface condition

Characteristics - Technical

Tensile strength, MPa	ASTM D-638	15 ± 3
Abrasion Resistance, 1000 cycle	ASTM D-4060	< 100 mg
Adhesion pull-off, MPa <ul style="list-style-type: none">On concreteOn Steel	ASTM D-4541	> 3 > 10
Elongation, %	ASTM D-638	3 ± 1
Water vapor transmission, 24 hrs, gm / m ²	ASTM E-96	0.10
Hardness Shore D, minute	ASTM D-2240	85 ± 5
Immersion test, 30 days <ul style="list-style-type: none">DIW1% H₂SO₄1% NaOH		No blistering / peeling / disbanding
Long term contact with potable water for human consumption	NSF/ANSI-61	No effect
Scratch Resistance, 1.5 kg load	IS:101	No failure
Compressive Strength (MPa)	ASTM C 109	70
Salt spray test, 5000 hr	ASTM D-2240	Passes

Application

- Excellent coating for internal / external lining of pipelines where abrasion / chemical resistance is of major concern.
- Being WRAS approved, excellent coating for internal / external linings of water pipelines.
- Internal coating for concrete / steel potable water storage.
- Sea water intake tunnels.

Advantages

- Solvent free, fast setting, high build-up epoxy.
- Excellent film build capabilities exceeding 400 micron in single coat, which can be extended with multiple passes.
- Excellent food grade properties.
- Excellent chemical / abrasion resistance properties. to the surface corrosion, protection properties.
- Good temperature / abrasion resistance properties.
- Very low permeability.

Application Methodology

➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease or other loose foreign particles by sand blasting / iron brush / compressed air.
- Prepare surface by mechanical grinding, shot blasting conforming to SA2½..

➤ Material Preparation

- Stir drums of each component thoroughly for uniformity. For best result, use a variable speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 400-600 rpm.
- Pre heat part-A @ 50-70 °C and Part-B @ 50-60 °C.

➤ Application of Material

- Apply **ShaliPoxy® 400** by plural feed airless spray gun to the required thickness on the prepared substrate.
- The tip pressure typically should be 2500-4000 psi (the tip pressure should be adjusted to achieve good atomization of the spray).
- Tip size typically should be 19 - 27 Thou orifice.

Cleaning & Maintenance

Clean all tools immediately after use with STP cleaner.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 200 L drum with 1 drum of Component B for every 3 drums of Component A.

Storage

Store in a cool dry place, under shade, away from heat.

Shelf Life

12 months in original, unopened, sealed condition.



STP
STP Limited
Advisory Cell
+91 81302 81114
Waterproofers to the Nation

STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Protective / Anti-Corrosive Coating
GARA (Grouts & Admixtures)
Sealant & Adhesives
Repairs & Rehabilitation
Epoxy Flooring

