

ShaliPoxy[®] CTE 403

2K High Build Solvent Free Coal Tar Epoxy Coating



Description

ShaliPoxy[®] CTE 403 is 100% solid, fast setting, spray applied, solvent free, two component, coal tar extended epoxy coating for internal / external lining of steel / concrete surface of pipes, vessels and other equipments used for water, mild chemical, oil and lubricant spillage.

ShaliPoxy[®] CTE 403 is spray applied by plural component airless spray gun.

ShaliPoxy[®] CTE 403 is solvent free protective barrier and is ideally suited for direct to metal coat where higher film thickness is required.

It conforms to AWWA C-210, SSPC Paint 16 and Corp of Engineers C 200/ C 200a

Characteristics – Physical

| | | | |
|---|------------------------------------|--|------------------------------------|
| Color | Brownish Black Glossy smooth | Ratio, volume | 3:1 |
| | | Sagging Test up to 420 micron DFT in single coat | Passes |
| | | Cross-cut test | Passes |
| Pot Life @ 28 OC,55% RH,100 g, minute | 30 ± 3 | Volume Solids | 100 % |
| Specific Gravity (Mixed) @ 27 °C | 1.40 ± 0.05 | Drying time @ 27 OC, 55% RH • Touch Dry • Hard Dry • Full Cure | Within 2 hr 8 – 10 hr 7 days |
| Theoretical Coverage *, m ² / L, 400 micron DFT | 2.50 | | |
| Application Temperature, °C | 10 – 60 with RH < 75% | | |

* Depending upon surface condition

Characteristics - Technical

| Property | Method | Result |
|--|-------------|--|
| Tensile strength, MPa | ASTM D-638 | 15 ± 3 |
| Abrasion Resistance, 1000 cycle | ASTM D-4060 | < 50 mg |
| Adhesion pull-off, MPa • On concrete • On Steel | ASTM D-4541 | > 3 > 10 |
| Elongation, % | ASTM D-638 | 10 ± 1 |
| Water vapor transmission, 24 hrs, gm / m ² | ASTM E-96 | 0.10 |
| Hardness Shore D, minute | ASTM D-2240 | 85 ± 5 |
| Immersion test, 30 days • DIW • 1% H ₂ SO ₄ • 1% NaOH | AWWA C-210 | No blistering / peeling / disbanding |
| Scratch Resistance, 1.5 kg load | IS:101 | No failure |
| Compressive Strength (MPa) | ASTM C 109 | 70 ± 5 |
| Salt spray test, 5000 hr | ASTM B 117 | Passes |

Application

- Excellent coating for internal / external lining of pipelines where abrasion / chemical resistance is of major concern.
- Coastal environment.

- Pulp & Paper industry.
- Excellent coating for internal / external linings of water pipelines.
- Internal coating for concrete / steel water storage.
- Sea water intake tunnels.

Advantages

- Solvent free, fast setting, high build-up epoxy.
- Excellent film build capabilities exceeding 400 micron in single coat, which can be extended with multiple passes.
- Excellent chemical / abrasion resistance properties.
- Very low permeability.

Application Methodology

➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease or other loose foreign particles by sand blasting / iron brush / compressed air.
- Prepare surface by mechanical grinding, shot blasting conforming to SA2½.

➤ Material Preparation

- Stir Component A thoroughly for uniformity. For best result, use a variable speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 400-600 rpm.
- Pre heat Component A @ 60 - 75 °C and Component B @ 50 - 60 °C.

➤ Application of Material

- Apply **ShaliPoxy® CTE 403** by plural feed airless spray gun to the required thickness on the prepared substrate.
- The tip pressure typically should be 2500-4000 psi (the tip pressure should be adjusted to achieve good atomization of the spray).
- Tip size typically should be 27 - 35 Thou orifice.

Cleaning & Maintenance

Clean all tools immediately after use with STP cleaner.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 200 L drum with 1 drum of Component B for every 3 drums of Component A.

Storage

Store in a cool dry place, under shade, away from heat.

Shelf Life

12 months in original, unopened, sealed condition.



Advisory Cell
STP Limited
+91 81302 81114
Waterproofers to the Nation

STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Protective / Anti-Corrosive Coating
GARA (Grouts & Admixtures)
Sealant & Adhesives
Repairs & Rehabilitation
Epoxy Flooring

