

TarFelt[®] LM

Water Based Bituminous Liquid Membrane



STP Limited

Description

TarFelt[®] LM is water based, cold applied, single component, elastomeric in-situ seamless monolithic coating. This unique system is ready to use acrylic modified bituminous liquid membrane.

Characteristics - Physical

Appearance	Viscous emulsion dries to black coating	Drying Condition	40 min for each coat depending on climatic condition
Application Temperature °C	> 5		8 -10
Specific Gravity, @ 30 °C	1.0 ± 0.01	Water Absorption, %	< 1
Viscosity on Brookfield @ 25 °C, cps	1600 - 1800	Theoretical Coverage, m ² / mm DFT, kg *	1.6

* Depending upon surface condition.

Characteristics - Physical

Properties	Standard	Results
Elongation after 7 days (1.50 mm film), %	ASTM C-412	190 - 200
Tensile Strength after 7 days (1.50 mm film), MPa	ASTM C-412	0.50
Crack bridging, mm, maximum	ASTM C-836	0.8
Pull off adhesion, MPa	ASTM D-4541	1.2
Hardness, Shore A (After 7 days)	ASTM D-2240	> 50

Application

- Corrugated asbestos roofs.
- Sunken.
- Rejuvenation of existing bituminous membrane – Hessian / HMHDPE based membrane.
- Residential terraces (flat / slope) in substitution of hessian / HMHDPE based membrane.

Advantages

- User friendly, Non-toxic, Green product.
- Excellent Waterproofing Characteristics.
- Good crack bridging property
- Cold applied and hence does not require heating.
- Monolithic and Seamless Membrane.
- Excellent bonding to concrete.
- Can be applied on moist surface also.
- Excellent vapour barrier.
- Good flexibility and does not crack on aging.
- Prevents growth of fungus, algae etc.

Application Methodology

➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet of dry air and clean the surface mechanically or by grinding to make it smooth before application.
- Repair all cracks by cutting "V" groove and fill with PMC mortar prepared in the ratio of ShaliCrete : Cement : Sand (1 : 2 : 5).

- Provide 50 mm x 50 mm coving made out of PMC mortar as above.

➤ **Material Preparation**

- Stir **TarFelt® LM** by a slow speed mixture (approx. 400 rpm) fitted with a suitable mixing paddle to ensure a homogenous mix.
- After stirring, wait for the product to settle in order to let entrapped air escape.

➤ **Waterproofing Application**

- Slightly damp the surface. Avoid standing water / ponding.
- Prime the surface with a mixture of **TarFelt® LM** and potable water in the ratio of 50 : 50 and apply @ 400 gm / m² of the mixture and allow it to touch dry.
- Apply first coat of **TarFelt® LM** @ 0.70 kg / m² by brush / roller / airless spray while the primed surface is tacky. For faster and smoother application, airless spray is preferred.
- Spread fiber glass net of 45 gsm with overlaps of 50 mm in both directions when the surface is still tacky.
- Allow 1st coat to dry for 10 – 12 hr.
- Apply second coat of **TarFelt® LM** @ 0.70 kg / m² by brush / roller / airless spray for final DFT of 1000 micron in two coats inclusive of fiber glass of 45 gsm (theoretical coverage depending on surface conditions).
- Sprinkle sand @ 200 gm / m² over the final **vertical** coating when the surface is still tacky to facilitate plastering.
- Ensure final curing time of 36 hrs before allowing / carrying out any further work.
- Conduct ponding test after 7 days of curing at ambient temperature.

➤ **Protection of Waterproofing**

- Spread ShaliGeoText 150 gsm with overlap of 50 mm in both directions on fully cured surface.
- Protect surface with 50 mm PCC admixed with ShaliPlast LW+ and a gradient of 1 : 100.

➤ **Rejuvenation of Existing Treatment**

- Clean existing surface thoroughly and remove all loose / foreign material.
- **TarFelt® LM** shall be applied on prepared surface as per above procedure.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapor.
- Wear suitable protective clothing, gloves and eye protection
- In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash immediately with plenty of clean water and seek medical advice.
- If swallowed seek medical attention immediately. Do not induce vomiting.

Packing

Available in 20 kg pack.

Storage

Store in a cool dry place, under shed, away from heat.

Shelf Life

12 months in original unopened sealed condition.



Advisory Cell
STP Limited
+91 81302 81114
Waterproofers to the Nation

STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Protective / Anti-Corrosive Coating
GARA (Grouts & Admixtures)
Sealant & Adhesive
Repairs & Rehabilitation
Epoxy Flooring

