# ShaliCool Guard





# **Description**

**ShaliCool Guard** (formerly known as ShaliCryl LM) is a single component, white colour, energy saving, UV resistant, elastomeric, micro fiber reinforced, heavy duty monolithic / seamless waterproofing liquid membrane having high mechanical strength and resistance to fungal growth. It is a two or three layer system ensuring proper build-up of the thickness and for a good cooling effect arising out of its high SRI. It conforms to ASTM D 6083.

#### **Product Information**

Colour, Form	White – Viscous Liquid	
Handling & Storage	Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.	
Packaging	Available in 5 kg and 25 kg container.	
Shelf Life	12 Months from the date of manufacture when maintain in protected storage in original unopened sealed condition at 5 - 40°C.	
Handling Precautions	As with all chemical products, care should be taken during use and storage to avoid contact with eyes mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. Keep away from children and animals. After opening the seal, always consume total material.	

## Technical Characteristics at 27°C, 55% RH

Property	Standard	Result	
Density, gm / cc		1.30 ± 0.03	
Viscosity, cps	1 1 1 1 1 1 1 1 1	5000 ± 2000	
Solar Reflective Index		105 ± 2	
рН		8 - 10	
Hardness, Shore A @ 7 days	ASTM D 2240	> 60	
Solid Content, %		61 ± 2	
Solar Reflectance (0 - 1 scale)	10/	0.82	
Emittance (0 - 1 scale)		0.92	
Relative Absorption, 7 days	/ //	3.7 - 5.0	
Water Absorption, %, 24 hours		0.2 - 0.4	
Theoretical Coverage, kg / m² @ 500 µ DFT *		1.0 - 1.10	
Elongation at break, %, 14 days	ASTM D 2370	300 ± 30	
Tensile Strength, N / mm <sup>2</sup> , 14 days	ASTM D 2370	1.70 ± 0.03	
Crack bridging, mm maximum, 10 cycles	ASTM C 836	1.0	
Pull Off Adhesion, after 7 days, MPa	ASTM D 454	1.6	
Water Vapor Transmission, gm / m <sup>2</sup> / 24 hrs.	ASTM E 96	21	
UV Resistance, 1000 hrs.	ASTM G 154	No Hardening / Chalking	
Resistance, Yeast and Mold	ASTM D 3273	Satisfactory	
* Depending upon surface condition, porosity, wastage during application			

<sup>\*</sup> Depending upon surface condition, porosity, wastage during application.

# **Field of Application**

- Flat / slopped roof with light foot traffic.
- Over brick-bat-coba.
- Being liquid, suitable for waterproofing of complicated geometrical structures like domes, arches, paraboloid and steeps rising on flashing.
- Very effective for crack repair in cementitious surfaces and waterproofing of vertical wall surfaces and over existing cementitious waterproofing treatments like brick-bat-coba, concrete screeds, acrylic coatings, etc.

#### **Advantages**

- Green product.
- Energy saving, heat insulating, UV resistant, user friendly, washable and easy to apply.
- Environmentally safe and non-polluting, Abrasion / dirt pickup resistant.
- Forms high mechanical strength, elastic & resilient coating enabling it to withstand structural movements.
- Higher tensile strength, tear resistance & bond strength with cementitious substrate.
- No additional protective coating is required for roof subjected to normal foot traffic.
- Can be coated on both sides of the roof top and ceiling to have better effect.
- Excellent wet adhesion strength with concrete and metal.

#### **Application Information**

✓ Substrate Temperature
 ✓ Ambient Temperature
 - +10°C Min / +40°C Max
 +10°C Min / +40°C Max

## **Application Methodology**

#### Surface Preparation

- Ensure that surface is free from all loose gravel, dirt and foreign matter with high- pressure wash. Before application surface should be totally dry, free from moisture, oil, grease, mill scale or rust.
- Do not apply during rains.
- Prior to application, repair torn flashings, loose brick, faulty covings or parapet walls to
  provide even surface. Large blisters and surface breaks shall be slit and opened for the
  release of entrapped moisture then cemented with Shalimar Dam-It wherever necessary.
- In case of old terraces with brick-bat-coba / screeds, ensure that substrate is firm and sound. Repair damage / hollow portions, sharp edges with ShaliFix® FRM 90 Surface cracks must be filled with PlastiSeal.
- Bitumen based waterproofing treatments must be completely removed by mechanical scarification or by any other effective mechanical method.

# Material Preparation

- Stir **ShaliCool Guard** by a slow speed mixture (approx. 400 rpm) fitted with a suitable mixing paddle to ensure a homogenous mix.
- After stirring, wait for the product to settle in order to let entrapped air escape.

## Application of Material

- Prime the surface with **ShaliCool Guard** diluted by addition of clean water in the ratio 1:1 and apply @ 3 4 m<sup>2</sup> / kg.
- Allow the primed surface to dry.
- Apply ShaliCool Guard using brush, squeeze, roller or Airless spray
- Ensure all corners / gaps / joints / protrusions / outlets are coated with two extra coats.

#### Precautions

- Do not open the containers until ready to use.
- Before carrying out waterproofing work on a finished roof, it must be ensured that the surface has adequate slope. Any stagnant water over the finished membrane shall result in development of algae, resulting in accelerated ageing of the membrane.

## Value base of product data

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control and different test methods.

#### **Health and Safety information**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent **Material Safety Data Sheet**.

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.

- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

# **Cleaning & Maintenance**

• Clean all tools immediately after use with STP Thinner only. Do not allow the material to harden. Hardened materials should be removed mechanically.







# **Product Range**

- Waterproofing and Insulation
   Road Surfacing
   Sealants and Additives
   Pipeline Coating
- Protective / Anti-Corrosive Coating Epoxy Flooring
- STP Limited Grouts / Admixtures RestoFix- Repair / Rehabilitation
  - Other Construction Chemicals



Advisory Cell: +91 81302 81114