

ShaliEPDM

Ethylene Propylene Diene Monomer Waterproofing Membrane



STP Limited

Description

ShaliEPDM is a synthetic single ply non-reinforced preformed Waterproofing Membrane in black colour. It is available in roll form with following dimensions. **ShaliEPDM** membrane is ideal for Waterproofing of Basement, Terrace and Pond Lining. It offers outstanding ozone and weather resistance delivering one of the longest service lives available. It Confirms ASTM D 4637 Type I.

Characteristics

Parameter	Result	ASTM Standard Type I	Test Method
Tensile Strength, MPa	>11	>9	ASTM D 412
Elongation, % Ultimate	>460	>300	ASTM D 412
Tear Resistance, kN / m	>30	27	ASTM D 624
Temperature Resistance, °C	- 40 to +110	-	-
Brittleness Point Max, °C	No crack	No crack at - 45	ASTM D 2137
Tensile Set, %	1.2	<10	ASTM D 412
Ozone Resistance, at 166 hrs. 50 pphm, 40°C or 50% extension	No cracks	No cracks	ASTM D 1149
Heat Aging Resistance 4 weeks @ 116°C Tensile strength, MPa Elongation Ultimate, % Tear Resistance, kN / m Linear Dimensional Change, %	10 ± 1 350 ± 30 23 ± 2 0.30 ± 0.05	8.30 200 21.9 ±1	ASTM D 412 ASTM D 412 ASTM D 624 ASTM D 1204
Resistance to Water Absorption, % After 7 days immersion at 70°C	0.30	< 8	ASTM D 471
UV Resistance (Ultraviolet exposure @ 80°C)	No crazing	No crazing	ASTM D 4637
Water Vapour permeance, Max, perms	0.1	--	ASTM E 96
Resistance to hydrostatic head, m, min	40	--	ASTM D 5385

Field of Application

- Waterproofing of Terrace or Podium
- Waterproofing of Underground structures and Basement
- Pond and Lake Lining at golf course, water preservation ponds, etc.

Advantages

- Available in various width and length from medium to large range
- No protection required for non-trafficable roof due to total UV resistant
- Easy to install
- High durability
- Can be used over a wide temperature range at cold and hot zone

Application Methodology

> Surface Preparation

Surface needs to be free from any defect like crack, undulation, foreign materials, grease and oil marks.

> Application of Material

ShaliEPDM can be loosely laid or fully adhered with **ShaliBond EPDM**, a rubber-based bonding adhesive overlap of 75 mm is provided on both directions for terrace application and overlap of 150 mm is provided for basement application. All overlaps can be sealed with bonding adhesive fully or with a splice tape.

> Pond Testing

- Water Ponding test can be conducted by sealing all drain outlet and ponding water to an average height of 50 to 75 mm for 72 hours and thereafter the same is released and checked for the roof / ceiling for leakage / seepage, if any.
- Water Ponding test is necessary to carry out before putting any protection over membrane to facilitate better accessibility, in case of any correction is desired.

> Protection over Membrane

- For trafficable roof membrane must be protected from any damage while in use a separation / protection membrane of **ShaliGeoText** of 300 GSM is laid over membrane, preferably loose, with an overlap of 50 mm on both directions and seal all the overlap fully to avoid any movement.
- Protection layer could be:
 - a. Loosely laid PCC tile of 1' x 1'
 - b. PCC of average thickness of 65 mm is laid with pre-cut of 10 mm x 10 mm while the concrete is green at every 4 m in both directions and gaps are filled with **ShaliSeal PU GG**, a single component Polyurethane Sealant.

Packing

Available in roll form of 30 m length and various width of 1.2 m, 3 m and 6 m width and in thicknesses of 1.2 mm, 1.5 mm and 2 mm.

Health & Safety

- Totally non-hazardous.
- However, it is preferred to use hand gloves and safety goggles while handling.
- Wash hands with water after handling.

Storage

- Store under shed and dry place.
- Keep it away from flame and fire to avoid damage.
- Keep the rolls vertically.

Shelf Life

There is no deterioration to material even after a prolonged storage, however, it is better to use within two years of manufacturing.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing & Insulation ■ Road Surfacing
- Sealants & Adhesives ■ Pipeline Coatings
- Protective/Anti-Corrosion Coatings ■ Epoxy and Flooring
- Grouts and Admixtures (GARA)
- RestoFix - Repair/Rehabilitation ■ Other Construction Chemicals



Advisory Cell: +91 81302 81114