

ShaliFix® SC 40

High Strength Quick Setting Repair Mortar



STP Limited

Description

ShaliFix® SC 40 is a single component portland cement based ready to use material to restore and repair concrete & masonry surface.

ShaliFix® SC 40 requires only addition of clean water to produce non-shrink, rapid-setting high strength repair mortar.

Characteristics – Physical

Appearance	Grey Powder
Water to Powder Ratio*, per 10 kg of Powder	1.2 - 1.4
Yield, m ³ / 10 kg bag	0.0045
Setting Time Minutes	50 - 60
Pot Life* at 30°C, minutes after mechanical mixing	8 - 10
Compressive strength, MPa, minimum, ASTM C 109 @ W:P = 0.12:1 <ul style="list-style-type: none">• 4 hrs.• 24 hrs.• 7 days• 28 days	32 45 52 60
Tensile Strength, MPa @ 28 days	>2.5
Flexural Strength MPa @ 28 days	>7
Permeability @ 28 days, DIN 1048 - 5	<15

*Water to powder ratio may vary depending consistency required for end use and climatic condition.

Note: The above test results were achieved under laboratory conditions. Tested at fluid consistency of 1.2 L per 10 kgs powder material

Application

- Structural repair for roadways, parking lot, ware house, bridges, dam, machinery, turbine floors
- Repair of damaged concrete in balconies, terraces, walls, beams
- Repair of spalling
- Repair of industrial shopfloor
- Road repair: Horizontal repairs, manholes placement (bedding and bonding) road / joint nosing
- Paving: Grouting pavement stone, joint filling
- Street Furniture: Fixing of road signage

Advantages

- Rapid hardening and return to service & thus reducing downtime.
- Application comfort in dangerous areas of use.
- Rapid re-opening to traffic, even at low temperature.
- Long service life of the repair.
- Does not contain any chlorides or additive which may contribute to corrosion of base structure.
- Low Permeability and higher durability.

Application Methodology

➤ Surface Preparation

- Surface to be plugged must be clean & free from dust, oils, grease curing compounds, residual mould oils or other contaminants that could impair adhesion.
- Preferably, cracks or holes should be cut to a minimum width and depth of 20 mm, cutting the side as square as practicable. Several hours prior to placing, the entire concrete substrate should be saturated with clean water. Remove any standing water.

➤ Priming

- Prime the surface with **ShaliSBR Latex** modified cement slurry @ 1:2 with addition of water to get a brushable consistency.

➤ **Material Preparation**

- In a mortar mixing machine initially add **ShaliFix® SC 40** followed by the addition of water in the W/P ratio 0.12. Mix thoroughly until a homogenous mixture is obtained.

➤ **Application of Material**

- After achieving consistency in the mixture, pour immediately in the repair joints & trowel or press into the joint.
- Use the entire prepared material within 5 minutes.
- Normal mortar curing process should be followed.

Cleaning

Tools and mixer may be cleaned with water before mortar paste has hardened, otherwise mechanical cleaning will be required.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 10 kgs moisture resistance bag.

Storage

Store in cool dry place, under the shed, away from heat.

Shelf Life

6 months in original unopened sealed conditions.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114