

# ShaliFloor® SL TC 3PU

3K Self Leveling Polyurethane Floor Top Coat



STP Limited

## Description

**ShaliFloor® SL TC 3PU** is three component polyurethane self-leveling flooring. It is solvent free system. **ShaliFloor® SL TC 3PU** is joint-less, monolithic, smooth, non-porous, hygienic, chemically resistant, besides being easy to clean and maintain. **ShaliFloor® SL TC 3PU** can be applied from 1 mm thickness to 2 mm thickness.

## Characteristics

Adhesion to concrete	Excellent	Shore D Hardness	60
Water absorption	Nil	Compressive Strength	50 N / mm <sup>2</sup>
Curing Time <ul style="list-style-type: none"><li>• Foot Traffic</li><li>• Vehicle Traffic</li><li>• Full Cure</li></ul>	24 hrs. 72 hrs. 7 days	Shrinkage	Nil
		Pot Life @ 30°C	20 minutes
		Substrate Temperature	10°C to 35°C
		Theoretical Coverage, kg / m <sup>2</sup> *	1.75 for 1 mm

\* Depending upon surface condition.

## Chemical Resistance

Acetic acid 10%	Resistant	Ammonia 5%	Resistant
Boric Acid 4 %	Resistant	Chlorine bleach 4%	Resistant
Chrome acid 10%	Resistant	Citric acid 10%	Resistant
Diesel	Resistant	Disinfectants	Resistant
Formaldehyde 37%	Resistant	Formic acid 10%	Resistant
Hydrochloric acid 10%	Resistant	Hydrogen peroxide 10%	Resistant
Lactic acid 25%	Resistant	Nitric acid 10%	Resistant
Petrol / Super	Resistant	Phosphoric acid 25%	Resistant
Phosphoric acid 50%	Resistant	Sodium lye 50%	Resistant

## Application

- Area requiring hygienic monolithic floor like, pharmaceutical industries, operation theatres & corridors in hospitals and nursing homes, laboratories, bottling plants, dairies & breweries, fermentation floors in tea garden, food processing - fisheries, meat processing, pickles, etc.
- Nuclear plants, computer and control panel rooms.
- Industries mainly aerospace including airport hangers, electric and electronic Industries, picture tube manufacturing plants, and textile mills, portable water and food storage.
- Automobile workshops.
- Oil Rigs.

## Advantages

- Better adhesion and flexibility
- Resists chemical

## Application Methodology

### ➤ Surface Preparation

- Prepare the surface by mechanical grinding or other suitable method.
- Remove dust, flakes, oil, grease or other loose foreign particles by sand blasting, iron brush or compressed air. Remove old painting using surface grinder.
- Remove old painting using surface grinder.
- For best bond, concrete surface must be slightly textured.
- Allow it to dry before priming.

### ➤ Material Preparation

- Mix **ShaliFloor® SL TC 3PU** component A (Resin) & C (Filler) thoroughly by using speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 1000 rpm till homogeneous mix is obtained. Then add component B (Hardener) slowly, ensuring complete dispersion. After all of component C has been added, mix for a minimum of 5 to 10 minutes.
- After stirring, wait for the product to settle in order to let entrapped air escape.

### ➤ Application of Material

- Prime concrete surface with **ShaliPrime® 2E** and allow it to dry for 6 - 8 hrs till it is touch dry.
- Pour the material on to the primed surface and spread the material with notched trowel to achieve the desired thickness.
- After spreading the material as per recommended coverage spike the surface with spike roller.
- Rolling should be done to achieve excellent finish as well as to remove the entrapped air.
- Prior to the application, during application and after application the substrate temperature should be above 10°C.

**SYSTEM DESCRIPTION:** Primer **ShaliPrime® 2E** at the rate of 0.3 - 0.5 kg / m<sup>2</sup>

### Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

### Packing

Available in 14 kg unit.

### Storage

Store in a cool dry place, under shed, away from heat.

### Shelf Life

12 months in original unopened sealed conditions.



**STP Limited**  
*Enhancing Structures' Life*

### Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



**Advisory Cell: +91 81302 81114**