

# ShaliPatch® EC 10

3K Self Leveling Modified Elastomeric Concrete



STP Limited

## Description

**ShaliPatch® EC 10** is a three component, cold applied, polymerized elastomeric concrete with excellent adhesion to substrate for

- crack filling ranging between 5 - 50 mm wide in concrete / flexible roads, and
- surface correction in concrete road / pavement.

**ShaliPatch® EC 10** is self-leveling, easily trowel-able into cracks and spall. It prevents percolation of water and other chemicals thus protecting it from wearing off.

## Characteristics - Physical

Colour	Black / Grey	Mixed density	1.80 ± 0.05
Drying Time, Touch, minutes	60	Application temperature, °C	5 to 45
Pot Life @ 30°C, minutes	6 ± 1	Chemical Resistance	Excellent
Solid % by volume	100	Curing Time <ul style="list-style-type: none"><li>• Over coat, hrs.</li><li>• Full cure, days</li></ul>	2 3
Open to traffic time, hrs., min.	1.5		
Mixing ratio, by wt., A : B : C	3.6 : 0.9 : 5.5		

## Characteristics - Technical

Property	Method	Result
Elongation after 7 days %, min	ASTM D 412	45 ± 5
Compression, MPa <ul style="list-style-type: none"><li>• 4 hrs.</li><li>• 1 day</li></ul>	ASTM D 695	3 8
Stress @ 5% deflection, 4 hrs., MPa	ASTM D 695	2.1
Tensile strength, 7 days, MPa	ASTM D 412	1.22 ± 0.07
Hardness, Shore D	ASTM D 2240	52 ± 3
Impact, -15°C, 1 lb., 10 ft	ASTM D 3029	No Cracking

## Application

- Excellent patching material for cracks and spalls on
  - Airport runways / Apron / Taxiways
  - PQC Roads / Bridges
  - Parking decks
  - Industrial floors
- Easy to use solution in retrofitting airport runways with lighting.

## Advantages

- High-load bearing capacity.
- Outstanding anti-spalling properties.
- Tough, Flexible and Durable.
- Rapid Cure time.
- Excellent resistance to chemical, saltwater, oil, acids, alkalis, crude oil, fuels and minerals.
- Compatible with both coal tar and asphalt emulsion-based sealers.
- Compatible with both concrete and bituminous pavement.
- Excellent to repair surface defects of the road.

## Application Methodology

### ➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet of dry air.
- Ensure that
  - The surface is structurally sound and dry.
  - In case of new concrete road, concrete is at least 28 days old.
  - Ambient temperature is not less than 5°C and not more than 35°C at the time of application.
  - There is no standing water in the area to be repaired or in the area of application.
  - Mechanically grinding the surface is acceptable only when sand blasting is not possible.
- Saw cut area to be repaired in geometrical shape leaving only sound concrete.

### ➤ Material Preparation

- Stir Component A thoroughly for uniformity.
- Mix entire pre-weighed component A (Resin) & entire pre-weighed component C (Aggregate) thoroughly by using speed drill mixer with a spiral type blade at the bottom of stirrer rod till homogeneous mix is obtained.
- Then add entire pre-weighed component B (Hardener) slowly, ensuring complete dispersion.
- Mix for a minimum of 2 - 3 minutes.

### ➤ Application of Material

- In case of concrete surface, prime the surface with **ShaliPrime® S / ShaliPrime® 2E SF**.
- Allow it to surface dry for 30 minutes to 4 hrs. depending on ambient condition.
- Pour mixed material in to the cracks, finish surface with trowel, if required.
- Allow it to dry at least two hours before opening traffic. Curing time will vary according to weather conditions.
- Do not install **ShaliPatch® EC 10** when any moisture is present or pavement temperature is below 5°C.

## Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of contact with eyes, wash immediately with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

## Packing

Box containing 5 Kg x 2 Packs. Each Pack 5 kg pack consists of Component A (Resin) - 1.80 kg, Component B (Hardener) - 0.45 kg and Component C (Aggregate) - 2.75 Kg.

## Storage

Do not allow product to freeze. Store in a dry area at temperatures between 10°C and 35°C in the original unopened containers.

## Shelf Life

12 months in original unopened sealed conditions.



**STP Limited**  
*Enhancing Structures' Life*

#### Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



**Advisory Cell: +91 81302 81114**