

ShaliProtek® 2E 65 MI



2K Epoxy Moisture Insensitive Phenolic Protective Coating

STP Limited

Description

ShaliProtek® 2E 65 MI is two components phenolic moisture insensitive amine based, self-priming epoxy coating suitable for application over damp concrete (green concrete), moist metal surfaces, RH exceeding 85% and on under prepared surface.

ShaliProtek® 2E 65 MI shows high impact resistance for protection of steel/concrete structures against splash and spillage of corrosive chemicals and solvents at higher temperature.

ShaliProtek® 2E 65 MI is an excellent coating system for secondary containment, solvent storage, pump pads, trenches, bridges and other high exposure zones.

Characteristics – Physical

Colour	Red / Grey	Service Temperature, °C, max	
Pot Life at 27 °C, minutes, 100 gm mix	55 – 65	• Immersion Condition	60
		• Under Insulation	230
Drying time, 30 OC, 85 % RT		Volume Solid, %, ASTM D 2967	68 ± 2
• Surface dry, hrs	3 ± 1	Theoretical Coverage*, m ² / L	6.6- 7.0
• Recoat time, hrs	6-18	100 Micron DFT	
• Full cure, days	3	Mixing Ratio, by volume	3 : 1
Scratch harness, 2 kg	Pass	VOC, gm / L	220

* Depending upon Surface Condition.

Characteristics - Technical

Property	Method	Result
Shore Hardness D, 7 Days	ASTM D 2240	55 - 60
Elongation, %	ASTM D 638	30 ± 3
Tensile Strength, N / mm ²	ASTM D 638	5 - 7
Specific Gravity	ASTM D 1475	1.35 ± 0.05
Impact Resistance, kg-inch	ASTM D 2794	150
Flash Point, OC	IS 101	> 30
Salt Spray, 2000 hrs	ASTM B 117	Pass
Cathodic Disbandment, mm	AWWA C 210	< 8
Abrasion Resistance, mg	ASTM D 4060	< 100
Chemical Resistance • 25% NaOH Solution • 20% HCl Solution • 30% H ₂ SO ₄ Solution • 10 % HNO ₃ Solution	In-House	Pass, No blister, wrinkling,
Adhesion N/mm ² • Green Concrete • Metal	ASTM D 4541	> 2.6 > 8.0
Flexibility, 1/8"	ASTM D 522	Pass

Application

- Piling and bridge under decks.
- Moist steel /moist concrete structures exposed to acid / alkali fumes emanating at high temperature, like in Ammonium Sulphate / Annealing / Acid Plants / Leather processing units, fertilizer plants etc.
- Anti-carbonation coating.

Advantages

- Excellent resistance to acid and alkali vapors.
- Low VOC material.
- Bonds well at low temperature & humidity.

Application Methodology

➤ Surface Preparation

- Remove dust, flakes, oil, grease or other foreign particles by jet or dry air and clean the surface by fresh water hosing prior to abrasive blasting to make it smooth before applying **ShaliProtek® 2E 65 MI**. Surface of steel must be prepared as per the NACE or SSPC guidelines at least to achieve SA 2½ level.
- For non-immersion purpose near white surface is adequate while for immersion purpose white metal surface is desired.

➤ Material Preparation

- Stir entire Component A thoroughly by using speed drill mixer with a spiral type blade at the bottom of stirrer rod till homogeneous mix is obtained.
- Add entire Component B in Component A. Both Component A & B comes in factory pre-weighed quantity in the ratios of 3 : 1 by volume.
- Mix to obtain a homogenous material.
- Wait for 5 minutes to ensure escape of entrapped air

➤ Application of Material

- Ensure that ambient temperature is in the range of 15 – 50 °C.
- Ensure that the application area is well ventilated
- Although **ShaliProtek® 2E 65 MI** is self-priming, it is recommended to prime the surface by ShaliPrime PUM for concrete surface and ShaliPrime Zn Ph for metal surface.
- Allow the primer to dry completely before applying **ShaliProtek® 2E 65 MI**.
- Apply **ShaliProtek® 2E 65 MI** by brush / spray with medium or short nap squeegee rollers.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapor.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 20 L unit pack with 15 L Component A and 5 L Component B.

Storage

Keep in cool and dry place, under shed, away from heat.

Shelf Life

12 months in unopened sealed condition.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114