

ShaliProtek[®] NES 60

2K Anti-Corrosive Chemical Resistant Novolac Based Phenolic Epoxy



Description

ShaliProtek[®] NES 60 is novolac based epoxy system for protection of concrete surface against splash and spillage of corrosive chemicals and solvents at higher temperature. It is an excellent coating system for secondary containment, solvent storage, pump pads, trenches, bridges and other high exposure zones.

Characteristics – Physical

Colour	White / Any Colour	Mixing Ratio, by volume	2 : 1
		Scratch hardness, kg	> 1.5
Service Temperature - Dry, °C	90	Volume Solid, %	62 ± 2
Surface drying time, hrs. @ 55% RB	2	Theoretical coverage*, m ² / L	6, DFT 100 micron 2.5, DFT 250 micron
Recommended DFT, micron	200 - 250		
Pot life @ 27°C, hrs., 100 gm mix	3 - 4	Recoat time, hrs.	10 - 12

* Depending upon surface condition.

Characteristics – Technical

Property	Method	Result
Shore Hardness D	ASTM D 2240	45 - 55
Elongation, %	ASTM D 638	15 - 20
Tensile Strength, N / mm ²	ASTM D 638	8 - 9
Impact Resistance	ASTM D 2794	20 kg-inch
Flash Point, °C	IS 101	> 30
Salt Spray, 2000 hrs.	ASTM B 117	Pass
Cathodic disbandment, mm	AWWA C 210	< 8
Abrasion resistance, mg	ASTM D 4060	98
Adhesion, N / mm ²	ASTM D 4541	> 2.6 - for concrete
Chemical Resistance <ul style="list-style-type: none">• 20% NaOH Solution• 25% NaOH Solution• 20% HCl Solution• 10% HNO₃ Solution• 30% H₂SO₄ Solution• 10% Phosphoric Acid• Diesel / Petrol		Pass, No blister No wrinkling

Application

- Excellent anti-corrosive coating for concrete flooring exposed to acid / alkali fumes emanating at high temperature, like in Ammonium Sulphate / Annealing / Acid Plants.
- Leather processing units, fertilizer plants, are some of the areas where **ShaliProtek[®] NES 60** will work efficiently.

Advantages

- Excellent resistance to acid and alkali vapours.
- Low VOC material.
- Bonds well at low temperature & humidity.
- Short re-coating time.

Application Methodology

➤ Surface Preparation

Remove dust, flakes, oil, grease or other foreign particles by jet or dry air and clean the surface to make it smooth before applying **ShaliProtek® NES 60**. Surface of steel must be prepared as per the NACE (National Anti-Corrosion Engineers) or SSPC (Steel Structure Protection Council) guidelines. For non-immersion purpose near white surface is adequate while for immersion service white metal surface is desired. Surface of steel and concrete must be free from dust, oil, soap and greasy material.

➤ Material Preparation

- Stir drums of each component thoroughly for homogeneousness with hand drill type stirrer to ensure dispersal of any settled filler for about 5 minutes for a 15 L pack. Then mix Component A and Component B in the ratio of 2 : 1 by volume. Stirring at slow speed for homogenization of the two components.
- Place the spiral blade at the bottom of the container before starting the mixer. This will help avoiding inducting air into the mass. Slowly move the stirrer head up to the surface while stirring. Do not remove the blade while still spinning. This procedure is continued for 5 minutes up and down to have a homogeneous mixing. Allow the mix 5 minutes, and then stir again gently with a hand stirrer to ensure uniformity and begin application.

➤ Application of Material

- Prime the surface by **ShaliPrime® 2E** for concrete surface and **ShaliPrime® Zn Ph** for metal surface.
- Allow the primer to dry completely before applying **ShaliProtek® NES 60**.
- Apply **ShaliProtek® NES 60** by brush or spray with medium or short nap squeegee rollers.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

ShaliProtek® NES 60 available in 15 L composite packs at the ratio of 2 : 1.

Storage

Keep in cool and dry place, under shed, away from heat and sun.

Shelf Life

12 Months in original unopened sealed condition.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing & Insulation ■ Road Surfacing
- Sealants & Adhesives ■ Pipeline Coatings
- Protective/Anti-Corrosion Coatings ■ Epoxy and Flooring
- Grouts and Admixtures (GARA)
- RestoFix - Repair/Rehabilitation ■ Other Construction Chemicals



Advisory Cell: +91 81302 81114