

ShaliKote® HR BT 260

Bituminous Cold Applied Emulsion For Protection Coating



STP Limited

Description

ShaliKote® HR BT 260 is an asphalt based Water emulsion material designed for coating Internal Casing Surfaces of Furnace, Boilers, Stacks behind mineral wool, brick, Castable & ceramic fibre linings.

ShaliKote® HR BT 260 remains plastic in order to accommodate movements of pipes or vessels, whose thermal insulation it protects. **ShaliKote® HR BT 260** can be used at elevated Temperature up to 210 °C with intermittent surges to 260 °C.

ShaliKote® HR BT 260 has excellent vapour barrier properties and resists UIC (under insulation corrosion).

Characteristics

Colour	Brown to Chocolate	Consistency	Pasty / Creamy
Flash Point, °C	> 200	Volume Solid, %	> 50
Application Temperature, °C	4 to 48	Dry Heat Resistance, °C	260
Film shrinkage, % loss thickness	48	Drying Time, hr	
DFT, mm, 2 coats	6	• Touch Dry	4
Specific gravity	1.30 ± 0.1	• Hard Dry	48
Theoretical Coverage*, kg / m ² , mm	2.2	Service Temperature, °C	260
		Application	By brush / Trowel

* Depending upon surface condition.

Application

- Internal Casing Surfaces of Furnace, Boilers, Stacks behind mineral wool, brick, Castable & ceramic fibre linings

Advantages

- Protects inner vessel casings from deterioration.
- Protects inner vessel casings from corrosive chemicals
- Excellent moisture barriers.
- High Temperature resistance
- Retains thermal efficiency during all weather conditions.
- Effective insulation material.
- Solvent free and hence eco-friendly and non-toxic.
- Effective in Under Insulation Corrosion Resistance.

Application Methodology

➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet of dry air and clean the surface mechanically or by grinding to make it smooth before application.

➤ Material Preparation

- Dilute **ShaliKote® HR BT 260** from its pasty consistency to that of light consistency by adding water in the ratio of 1:1.

➤ Application of Material

- Apply this diluted material on the surface as primer.
- Allow it to dry.

- Apply first coat of **ShaliKote® HR BT 260** when the primed surface is dry and wait for coating to change black from its original brown colour and allow **ShaliKote® HR BT 260** to break.
- Allow it to dry for 24 hrs.
- Apply second coat.
- Sprinkle sand @ 200 grm / m² over the final coating when the surface is still tacky.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water.
- Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 20 kg containers.

Storage

Keep in cool and dry place, in air tight containers, under shed, away from heat.

Shelf Life

6 months in original unopened sealed conditions.



Advisory Cell
STP Limited
+91 81302 81114
Waterproofers to the Nation

STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Protective / Anti-Corrosive Coating
GARA (Grouts & Admixtures)
Sealant & Adhesives
Repairs & Rehabilitation
Epoxy Flooring

