

# ShaliPrime<sup>®</sup> Zn Ph

2K Anti-Corrosive Zinc Phosphate Primer



STP Limited

## Description

ShaliPrime<sup>®</sup> Zn Ph is a two component, polyamide cured, zinc phosphate anti-corrosive epoxy primer for metal surfaces.

ShaliPrime<sup>®</sup> Zn Ph does not consist of any lead pigment.

## Characteristics

Colour	Grey	Pot Life, 30 °C, hr	4
Theoretical Coverage*, m <sup>2</sup> / L	5.00 – 8.00	Recoating time, 30 °C, hr	8 - 80
DFT*, micron	60 – 100	Curing Time Full Cure, days	7
Application Temperature, °C	>10 to < 110	Substrate Temperature, °C	>10 to < 110
Drying time, 30 °C		Adhesion, Mpa	> 7
• Touch dry, minute	35	Volume solid, %	48 – 50
• Hard dry, hrs	9	Density, grm / cc	1.35 ± 0.05
• Overcoating, hrs	8 - 10	Lead pigment	Nil

\* Depending upon surface condition.

## Application

- Suitable for use on blast cleaned steel where a complete epoxy system is required. It is suitable as a patch primer for treatment of manually prepared steel.

## Advantages

- Resists most chemical environment when used with recommended topcoats.
- Resists water / corrosion.
- Provides good anti-corrosion protection.
- Facilitates adhesion of finish onto difficult substrates.
- Non-toxic, safer to use as compared to chromate version.

## Application Methodology

### ➤ Surface Preparation

- Remove dust, flakes, or other foreign particles by jet or dry air and clean the surface mechanically or by grinding to make it smooth before application.
- Thoroughly dust down the surfaces.
- Remove majority of rust scales from surface of rusting steel structure / reinforcement by wire brush, chipping or grinding.
- Ensure that the substrate temperature is in the range of 10 °C – 110 °C.
- Apply ShaliRustOff on the surface where wire brush is not reachable and allow the surface to dry for 30 minutes.

### ➤ Material Preparation

- Stir entire Component A thoroughly by using speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 300 - 400 rpm till homogeneous mix is obtained.
- Add entire Component B in Component A. Both Component A & B comes in factory pre-weighed quantity in the ratios of 4 : 1 by volume.
- After stirring, wait for 5 minutes to ensure escape of entrapped air.

### ➤ Application of Material

- Apply **ShaliPrime® Zn Ph** by brush / roller / spray. When applied by airless spray gun, ensure that the minimum working pressure of 140 kg / cm<sup>2</sup> with a spray tip size 0.43 – 0.53 mm and a spray tip angle of 65° C.
- Ensure that the base and the hardener are at the minimum temperature of 15 °C when mixed for satisfactory spray application.
- **ShaliPrime® Zn Ph** may be over coated with conventional paints or two-pack epoxy paints and polyurethane. Over-coating can be done after 8 - 10 hrs; however,
- It is recommended to coat the finish paint after 12 - 24 hrs of application of primer to obtain superior performance.

### Health & Safety

- The product should not come in contact with the skin and eyes, or be swallowed.
- Ensure adequate ventilation and avoid inhalation of vapours as some people are sensitive to resins, hardeners and solvents.
- Wear suitable protective clothing, gloves and eye protection.
- In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately - **do not** induce vomiting.

### Packing

Available in 15 L container consist of Component A 12 L and Component B 3 L.

### Storage

Store in a cool dry place, under shed, away from heat.

### Shelf Life

12 months in original unopened sealed condition.



**STP Limited**

*Enhancing Structures' Life*

### Product Range

- Waterproofing & Insulation
- Road Surfacing
- Sealants & Adhesives
- Pipeline Coatings
- Protective/Anti-Corrosion Coatings
- Epoxy and Flooring
- Grouts and Admixtures (GARA)
- RestoFix - Repair/Rehabilitation
- Other Construction Chemicals



**Advisory Cell: +91 81302 81114**