

ShaliProtek® HR BT 100

Heavy Duty Anti-Corrosive Bituminous Paint for Ductile Iron



Description

ShaliProtek® HR BT 100 is a heavy duty bituminous coating which gives a smooth black egg shell mat finish. The coating shall not impart any taste or odour to water, and it is non toxic conforms to BS 3416 /1991, Type II (For Portable Water)

It shall provides highly durable protective coating to prevent corrosion or rust on Ductile Iron , Mild steel structures & Waterproof to the concrete surfaces.

Characteristics

Drying Time, Max • Surface Dry • Hard Dry	15+/-5 minutes Max 8 hrs	Consistency	Smooth, uniform Brushable and and sparyable
Finish	Smooth , Egg shell to mat	DFT, Micron	70– 100
Viscosity @ 30 °C, B 4 cup	120 – 180 sec	Colour	Black
Volatile content, % by weight	Max 40 %	Flash Point	> 23°C
Theoretical Coverage, Sqmt/Lit	5 -6	Specific Gravity	1.2+/-0.2

* Depending upon surface condition

Application

- External surfaces of Ductile Iron Pipes.
- External surface of any MS steel structure.
- External concrete surface

Advantages

- Easy application by brush / spray gun. It dries rapidly leaving black egg shell mat finish.
- Resistant to water, acids / alkalis and natural salts.
- Does not crack due to weathering, expansion or contraction.
- Give highly durable protective air-tight coating to prevent corrosion or rust on iron, steel Ductile Iron & concrete surfaces against air, moisture, sea water.

Application Methodology

➤ Surface Preparation

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet of dry air and clean the surface mechanically or by grinding to make it smooth before application.

➤ Material Preparation

- Stir **ShaliKote BT 100** thoroughly to achieve homogenous mix by a mechanical drill.

➤ Application of Material

- Apply **ShaliKote BT 100** on dried and Cleaned surface by brush or spray gun.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.

- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water.
- Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 20 Lits and 200 Lits container.

Storage

Keep in cool and dry place, under shed, away from heat.



STP Limited
Advisory Cell
+91 81302 81114
Waterproofers to the Nation

STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Protective / Anti-Corrosive Coating
GARA (Grouts & Admixtures)
Sealant & Adhesives
Repairs & Rehabilitation
Epoxy Flooring

